

JUNTEADOR EXTRAFINO

VISANJUNTEX



Characteristics

Made with extremely fine aggregates to achieve strong adhesion in sealing joints from 0 to 2 mm, when materials are installed edge-to-edge or flush, using all types of rectified materials (porcelain, clinker, marble, and granite). Suitable for high-traffic, commercial, and residential environments in both indoor and covered outdoor areas (not exposed to sun, rain, or frost). Available in white, beige, gray, and black. All our joints feature a water-repellent effect and do not undergo volume changes after application.

Applications

Jointing for floors and wall coverings in commercial and residential environments (hotels, private residences, etc.).

Storage

The product should be kept in its original packaging and stored in a dry place, allowing it to be stored for at least two years.

Presentation

Heat-sealed 5 kg bags. Box of 6 bags (30 kg). Pallet of 40 boxes.

Instructions for use

- Knead by hand or machine at low speed until achieving a smooth, consistent, and lump-free texture.
 - Avoid applying in extreme temperatures, below 5°C or above 30°C.
 - Let the mixture rest for 5 minutes, stir, and then apply.
 - Preferably apply with a rubber trowel or spatula.
 - Fill the joint, leaving a compact and uniform surface.
 - Once the initial gloss disappears, remove any excess product, ideally with a damp sponge.
 - Perform a final cleaning when the joint has hardened.
 - Ensure the surface is clean and free of laitance and release agents.
 - Do not apply on wet surfaces or those with loose parts.
 - Avoid application in extreme weather conditions.
 - Wait time before finishing: 20 - 30 minutes.
 - Ready for service after 24 hours (48 hours for tanks and pools).
 - Walkability: approximately 3 hours.
- Jointing after installation:
- For walls bonded with standard adhesive: 4 - 8 hours.
 - For walls bonded with quick-setting adhesive: 1 - 2 hours.
 - For walls with mortar: 2 - 3 days.
 - For floors bonded with standard adhesive: 24 hours.
 - For floors bonded with quick-setting adhesive: 3 - 4 hours.
 - For floors with mortar: 7 - 10 hours.

PHYSICAL AND CHEMICAL PROPERTIES

Classification according to UNE EN 12888	CG 2 WA
Appearance	White or colored powder
Mixing Water	35 ± 1 %
Bulk Density in Powder Form	1,1 g/cm ³
Bulk Density in Paste Form	1,4 g/cm ³
Abrasion Resistance (UNE-EN 12808-2)	≤ 2000 mm ³
Compression Strength (UNE-EN 12808-3)	≥ 15 N/mm ²
Flexural Strength (UNE-EN 12808-3)	≥ 3,5 N/mm ²
Shrinkage Determination (UNE-EN 12808-4)	≤ 2 mm/m
Water Absorption at 30 min (UNE-EN 12828-5)	≤ 2 g
Water Absorption at 240 min (UNE-EN 12808-5)	≤ 5 g
Yield*	0,3 - 0,4 Kg/m ²
Working Time of Paste**	Approx. 60 min

* Test conducted on a 1 mm thickness, depending on the joint width.

** Test conducted under normal environmental conditions of 23°C and 55% relative humidity. Test conducted on a surface with a thickness of 5 mm.

Tile Format	Yield	
	1 mm	2 mm
15 x 15	0.052	0.140
15 x 20	0.046	0.092
20 x 20	0.042	0.084
25 x 25	0.033	0.066
30 x 60	0.021	0.042
60 x 60	0.012	0.024
60 x 90	0.008	0.016

